

TECHNICAL SHEET

Ag30Sn



Product name

Ag30Sn

Class of product

Silver based brazing alloy, cadmium-free

Corresponding standards

DIN8513 L-Ag30Sn

EN1044 AG 107

AWS A5.8-04 ---

Nominal composition (weight %)

Ag: 30

Cu: 36

Zn: 32

Sn: 2

Physical characteristics

Melting range (Solids – Liquids): 650 – 750 °C

Brazing temperature: 760 °C

Density: 8,8 g/cm³

Tensile Strength: 48 kg / mm²

Range of application:

Ag30Sn is a low melting, cadmium-free, silver brazing alloy with good flow characteristics.

It can be used to join ferrous, non ferrous and dissimilar metals and alloys with close joint clearances, such

as steel, copper, copper alloys, nickel, nickel alloys.

Brazing procedures range from manual to induction techniques.

When brazing in an oxidizing environment a proper flux should be used.

Typical applications are in the automotive, electric, air conditioning and refrigeration industries.

Characteristics Make-up:

Rods: Ø 0,5 _ 4,0 mm Length: 500 / 1.000 mm

Flux Coated Rods: Ø 1,5 _ 3,0 mm

Wires: Ø 0,25 _ 3,0 mm (spooled and coiled)

Strips: Thickness: 0,1 _ 1 mm Width: 1,5 _ 65 mm

Rings

Performs from Wire and from Strip

Pastes & Powders

Other dimensions are available upon request

The above data are subject to change without notice by Spring.

SPRING WELDING ALLOYS

Hangzhou City, Zhejiang, China

Phone – 0086-13588821060

info@springwelding.com - www.springwelding.com