## TECHNICAL SHEET

# Ag40Sn



\_\_\_\_\_\_

#### **Product name**

Aq40Sn

#### **Class of product**

Silver based brazing alloy, cadmium-free

### Corresponding standards

DIN8513 L-Ag40Sn EN1044 AG 105 AWS A5.8-04 BAg-28

#### Nominal composition (weight %)

Ag: 40 Cu: 30 Zn: 28 Sn: 2

#### Physical characteristics

Melting range (Solids - Liquids): 640 - 700 °C

Brazing temperature: 710 °C

Density: 9,1 g/cm3

Tensile Strength: 44 kg / mm2

#### Range of application:

Ag40Sn is a low melting, cadmium-free, silver brazing alloy with good flow characteristics. It can be used to join ferrous, non ferrous and dissimilar metals and alloys with close joint clearances, such

as steel, copper, copper alloys, nickel, nickel alloys.

Brazing procedures range from manual to induction techniques.

When brazing in an oxidizing environment a proper flux should be used.

Typical applications are in the automotive, electric, air conditioning and refrigeration industries.

#### **Characteristics Make-up:**

Rods: Ø 0,5 \_ 4,0 mm Length: 500 / 1.000 mm

Flux Coated Rods: Ø 1,5 \_ 3,0 mm

Wires: Ø 0,25  $\_$  3,0 mm (spooled and coiled) Strips: Thickness: 0,1  $\_$  1 mm Width: 1,5  $\_$  65 mm

Rinas

Performs from Wire and from Strip

Pastes & Powders

Other dimensions are available upon request

The above data are subject to change without notice by Spring.

\_\_\_\_\_\_

#### **SPRING WELDING ALLOYS**

Hangzhou City, Zhejiang, China Phone – 0086-13588821060

in fo@springwelding.com-www.springwelding.com